

CREATED:	AEM	DATE:	25/09/2018	VERSION:	8
-----------------	------------	--------------	-------------------	-----------------	----------

PRODUCT REFERENCE:	PN0766
---------------------------	---------------

NOMENCLATURE:	GP-B-39-S33
DESCRIPTION:	39 gsm Bleached Greaseproof with 2 side silicone coated

Specification values in bold, **N.B.** only relevant tests will be measured

PHYSICAL CHARACTERISTICS	UNIT	VALUE	TOLERANCE	TEST METHOD
Total Substance	gsm	39	+/- 5%	ISO 536
Thickness	µm	44	+/- 10%	ISO 534
Tearing Resistance	mN	MD200/CD220	For info only	ISO 1974
Water absorptiveness Cobb (60 s.)	%	11	For info only	ISO 535

OTHER CHARACTERISTICS	UNIT	VALUE	TOLERANCE	TEST METHOD
Recommended process Temperature	°C	210°C max	For info only	-

FOOD CONTACT STATUS	Suitable for direct food contact.
----------------------------	-----------------------------------

GENERAL STATEMENT

Since the end use of this product is beyond our direct control, we expect that customers will satisfy themselves that the product is suitable for their end use. Unless specifically negotiated, we reserve the right to use raw material from more than one source whilst maintaining a commercial match within the terms of this data sheet.

Sheet, reel and core sizes should be specified on the official order and will be subject to normal British Paper Trade tolerances.

SHELF-LIFE

The shelf life of this product supplied by Advanced Coated Products Limited is 1 year if stored as indicated below:

- Stored in original packaging and away from dirt, dust and contamination
- Stored in a cool, dry environment (Temp 5-25oC; RH 30-50%)
- Stored with no exposure to direct sunlight (UV light)